



This product is not compliant for sale and use in CA CT DE ME MD MA NH NJ NY PA VA DC IL MI OH IN.

**FOR INDUSTRIAL AND INSTITUTIONAL USE ONLY**

**DANGER:** Contains Petroleum Distillate (64742-89-8), Zinc Dust (7440-66-6), and Modified Oil (Mineral Spirits) (8052-41-3). Do not take internally. Avoid contact with eyes. Avoid breathing vapors. Keep away from heat, sparks and open flame.

**FIRST AID:**

**IF EYE CONTACT:** Flush with large amounts of cool running water for at least 15 minutes while holding upper and lower lids open. If irritation persists get medical attention immediately.

**IF SKIN CONTACT:** Wash with soap and water. If irritation persists seek medical attention.

**EXCESSIVE INHALATION:** Remove to fresh air. Seek medical attention immediately. If breathing stops give artificial respiration.

**IF INGESTED:** Do not induce vomiting. Seek medical attention immediately.

**HMIS RATING:** Health, 1; Flammability, 3; Reactivity, 1; Personal Protection, B.

**HANDLING AND STORAGE:**

Keep container closed except when in use. Do not store in unmarked containers. Store in a cool, dry place. Do not cut or weld on or near this container even when empty.

**KEEP OUT OF REACH OF CHILDREN**

For further information consult Material Safety Data Sheet



**COLD ZINC GALVANIZE**

295805

Equivalent to Hot Dip  
Corrosion-Proofs Metal  
Prevents Rust Creepage

**DANGER:** FLAMMABLE LIQUID.  
VAPOR HARMFUL.  
HARMFUL OR FATAL IF SWALLOWED.  
SEE OTHER CAUTIONS ON SIDE PANEL.

NET CONTENTS: 5 GALLONS



P.O. Box 667770 • Pompano Beach, FL 33066  
www.terandstore.com

Metallic Coatings (MCP) Do Not Exceed  
80% VOC or 1.90 MIR.

A revolutionary, one component, ready-to-use product that requires no measuring or addition of other ingredients. Produces a tough, uniform and adherent zinc-rich film.

On metal surfaces, seals out moisture and prevents corrosion by sacrificial galvanic action. It is highly resistant to water, acid and salt atmospheres.

A long-term rust preventative which flows and coats smoothly and evenly. Can be painted over when dry. A high viscosity formulation in which the micron size zinc particles remain suspended for long periods of time.

**TYPICAL USES:** Oil Rigs, Signs and Fencing, Tanks and Piping, Structural Steel and Wire, Fans, Ducts and Culverts, Dairy Equipment, Air Conditioning Units, Road and Farm Equipment, Shipyards, Welding and Mining.

**DIRECTIONS:**

1. Clean surface thoroughly. Remove grease and oil with degreasing solvent. Remove all paint with paint remover, then clean surface with paint thinner. Remove all loose rust. Wire brush light rust. Sandblast heavy rust or mill scale. Metal that is to be later submerged under water requires fine sandblasting.
2. Agitate before and during use.
3. Do not thin or mix with other chemicals.
4. Creamy suspension lends itself to brush coating as well as spraying. Dries to touch in 15 minutes. Second coat may be brushed on after waiting at least 24 hours. For maximum resistance to salt spray, allow to air dry and cure for several days. Several thin coats are better than one heavy coat. Drying can be accelerated, if necessary, by blowing hot air over surface or baking in oven.
5. Always keep container closed when not in use to prevent evaporation and contamination.